Unit 4, Trevallyn Park East,
Hyskraan Close,
Kya Sands, Randburg

PO Box 70, Olivedale, 2158
Reg: 1991/031153/23
info@samson.co.za

Specification: Samson SDS Dry-Shake

(Standard Dry Shake)

TENDER BOQ				
Item	Bill description	Unit	Bill quantity	Amount
1.1.	Apply **SAMSON SDS** dry shake floor hardener in a colour of choice to concrete surface beds at installation phase, at rate of 7kg / m². Curing with **FP Cure** curing compound at a rate of 7-10m² /L, subsequently removing curing compound with **PolyStripper** at a rate of 5 – 8 m² / L. Followed by **SAMSON HC Densifier** to be applied at a rate of 8 – 10 m² /L and washed off after the chemical reaction has taken place. Once surface bed is below 5% moisture, apply **MM Sealer Siloxane** by microfibre mop at a rate of 8 – 10 m² / L in two coats. All in accordance with the manufacturer's instructions. Request the Samson detailed method statement if needed. Supplier: SAMSON Technologies Contact: 011 462 2666 or info@samson.co.za	m²	574	